




























Reference Standard: EN 14411: 2012 Ceramic Floor and Wall Tiles: Definitions, Classification, Characteristics and Marking

Product Type: Dry Pressed: Group Bla UGL

REVIGRÉS Reference: COPPER NAT

Use: Internal and External Wall and Floor Tiles

TEST METHODS	STANDARD AND TEST VALUE	DECLARED VALUES
Length and Width	ISO 10545-2  ± 0,5%	± 0,2%
Deviation of mean thickness from manufacturing thickness	 ± 5%	± 5%
Straightness of the edges	ISO 10545-2  ± 0,5%	± 0,3%
Orthogonality	 ± 0,6%	± 0,3%
Surface Flatness	 ± 0,5%	± 0,3%
Surface quality (% defect free)	 ≥ 95%	Compliant
Water Absorption	ISO 10545-3  < 0,5%	< 0,05%
Bending Strength (N)		
Thickness ≥ 14 mm	ISO 10545-4  ≥ 1300	> 6500
8,5 mm < Thickness < 14 mm	ISO 10545-4  ≥ 1300	> 3500
7,0 mm ≤ Thickness ≤ 8,5 mm	ISO 10545-4  ≥ 1300	> 2000
Rupture Modulus (N/mm ²)	 > 35	> 45
Resistance to deep abrasion (removed Volume/mm ³)	ISO 10545-6  < 175	< 120
Coefficient of Linear Thermal expansion (with atmospheric temperature up to 100 °C)	ISO 10545-8  Test method available	≤ 8,0x10 ⁻⁶ / °C
Resistance to Thermal shock	ISO 10545-9  Required	Resistant
Resistant to frost	ISO 10545-12  Required	Without visible defects
Resistance to Acids and high concentrations Bases	ISO 10545-13 	The producer declares the classification
Resistance to Acids and low concentrations Bases		Class HA
Resistance to household chemicals and swimming pool water additives		Class LA
Resistance to staining	ISO 10545-14  Mín. Class B	Class A
Resistance to staining	ISO 10545-14  Test method available	Class 5
Antislip Resistance	DIN 51130  Máx. R13	Test available
Antislip Resistance	DIN 51097  Máx. C	Test available
Antislip Resistance	ENV 12633  Máx class 3	Test available
Antislip Resistance	BS 7976  Test method available (PTV)	Test available
Antislip Resistance	ANSI A137.1  Test method available (DCOF)	Test available
Resistance to heavy shock	UPEC CSTB  UPEC	Level 0 a 5
Reaction to fire	EN 13823 EN 9239-1  A1 _{FL}	Class A1 _{FL} / Class A1

*Technical specifications are only valid for the products classified as 1st choice.

001/10